



## Technical Data Sheet

**S 40**  
Version Nr. 3

Glass Fibre Netting			
	Characteristic	SSA - 1111 - 340 - SM	Test method
1.	Size of hole, mm	~ 9	Comp. method PP - Q - S 05
2.	Weave	Leno	
3.	Construction of fabric, tex	warp: EC 11 - 544 Z 28 weft: EC 19 - 1200	DIN EN 12654
4.	Thread count per 10 cm	warp: 32 +/- 2 weft: 9 +/- 1	DIN 53853
5.	Width, cm	100 + 1/- 0	DIN EN 1773
6.	Weight, g/m <sup>2</sup>	≥ 300	DIN EN 12127
7.	L.O.I., %	≥ 15	DIN ISO 1887
8.	Tensile strength, N/50 mm	warp: ≥ 4800 weft: ≥ 3000	EN ISO 13934.1
8.1	Tensile strength, N/50 mm after ageing ( ETAG 004)	warp: ≥ 2400 weft: ≥ 1500	
9.	Roll length, nom., m	50	

### Packing, Storage, Transporting

#### Packing:

- netting wound on the core with inside diameter 76 mm,
- each roll wrapped in the plastic, put in the carton and fastened on the wooden pallet or rolls wrapped in the plastic and fastened on the wooden pallet without carton

#### Transporting, Storage:

- goods have to be stored and transported in the producer's packing,
- clean and dry storage.